



DUNWANDIGE KRIMPKOUS NF301 OP ROL

KEURINGEN  

KENMERKEN  Polyolefin IN BOX dunwandig en flexibel
Krimpverhouding 3:1 Rek 300 % / Min. Krimptemperatuur 90°
Zonder lijm / vlamdovend
KLEUR : ZWART

Verrijgbaar in kleuren : Disponible en couleurs :	Zwart/Noir		Voor	Na	OP ROL		
	Artikelnummer	Ean nummer	Krimp In mm		Pack	Overdoos	Type
Grijs							
Rood	702-WE-POZW-R-0030	5420023931658	3	1	200	1000	stock
Geel	702-WE-POZW-R-0048	5420023931672	4,8	1,6	200	1000	stock
Blauw	702-WE-POZW-R-0060	5420023931696	6	2	150	750	stock
Wit	702-WE-POZW-R-0090	5420023931719	9	3	150	750	stock
Bruin	702-WE-POZW-R-0120	5420023931733	12	4	100	500	stock
Groen	702-WE-POZW-R-0180	5420023931757	18	6	50	250	stock
GEEL/GROEN GESTREEPT	702-WE-POZW-R-0240	5420023931771	24	8	50	250	stock
Transparant	702-WE-POZW-R-0390	5420023931795	39	13	25	125	stock




Grijs	702-WE-POGS-R...
Rood	702-WE-PORO-R...
Geel	702-WE-POGE-R...
Blauw	702-WE-POBL-R...
Wit	702-WE-POWI-R...
Bruin	702-WE-POBR-R...
Groen	702-WE-POGR-R...
Transparant	702-WE-POTR-R...
GEEL/GROEN GESTREEPT	702-WE-POGG-R...

- **NF301**
 - The same as NF201, but than in a 3:1 ratio, with fewer sizes, the total range of applications can be covered. 3:1 ratio we note in growing demand the use in (assortment -) boxes, length boxes, although in short, there were people with a limited qty. of products, are looking for a solution.

DUNWANDIGE KRIMPKOUS NF301 IN BOX

Verrijgbaar in kleuren : Disponible en couleurs :	Zwart/Noir		Voor	Na	IN BOX		
	Artikelnummer	Ean nummer	Krimp In mm		Box / Overdoos	Inhoud	Type
Grijs							
Rood	702-WE-POZW-B-0030	5420023931665	3	1	1 / 36	15.0 mtr	stock
Geel	702-WE-POZW-B-0048	5420023931689	4,8	1,6	1 / 36	12.0 mtr	stock
Blauw	702-WE-POZW-B-0060	5420023931702	6	2	1 / 36	10.0 mtr	stock
Wit	702-WE-POZW-B-0090	5420023931726	9	3	1 / 36	10.0 mtr	stock
Bruin	702-WE-POZW-B-0120	5420023931740	12	4	1 / 36	7.0 mtr	stock
Groen	702-WE-POZW-B-0180	5420023931764	18	6	1 / 36	4.0 mtr	stock
GEEL/GROEN GESTREEPT	702-WE-POZW-B-0240	5420023931788	24	8	1 / 36	3.0 mtr	stock
Transparant							



DISPLAYREKJE



Grijs	702-WE-POGS-B...
Rood	702-WE-PORO-B...
Geel	702-WE-POGE-B...
Blauw	702-WE-POBL-B...
Wit	702-WE-POWI-B...
Bruin	702-WE-POBR-B...
Groen	702-WE-POGR-B...
Transparant	702-WE-POTR-B...
GEEL/GROEN GESTREEPT	702-WE-POGG-B...





NF 301

3:1 shrink ratio
 shrink temperature >90° C
 self extinguishing (colours only)
 operating temperature -55° C to +135° C



Flexible tubing which offers a shrink ratio of 3:1. The high expansion ratio is designed for use when wide ranging substrate diameters need to be covered. NF 301 is suitable for applications such as marking, strain relief, mechanical protection and identification.

Size mm	Minimum ID Supplied mm	Maximum ID Recovered mm	Wall Thickness Recovered (NOM) mm
1.5/0.5	1.5	0.5	0.45
3/1	3.0	1.0	0.55
4.8	4.8	1.5	0.60
6/2	6.0	2.0	0.70
9/3	9.0	3.0	0.70
12/4	12.0	4.0	0.70
18/6	18.0	6.0	0.80
24/8	24.0	8.0	1.00
39/13	39.0	13.0	1.15

SPECIFICATIONS

SAE-AMS-DTL-23053/5 Class 1 (colours)*
 SAE-AMS-DTL23053/5 Class 2 (clear)*
 UL 224, 125° C - UL cert. E228117¹*
 CSA C 22.22 No. 198.1-98, OFT¹*
 (except ¹ clear)

STANDARD COLOURS

black, white, red, blue, yellow

NON STANDARD COLOURS

clear, pink, violet, green, brown, orange, grey, gys (green/yellow striped) and other colours available on request

PROPERTIES

Physical:

tensile strength
 elongation at break
 longitudinal change
 water absorption
 specific gravity

Thermal:

continuous operating temperature
 minimum shrink temperature
 heat shock 4 hours at 250° C
 heat aging 168 hours at 175° C
 low temperature flexibility -55° C
 flammability

Chemical:

fungus resistance
 chemical resistance
 copper corrosion

Electrical:

dielectric strength
 volume resistivity

TEST METHOD

ASTM D 638
 ASTM D 638
 ASTM D 2671
 ASTM D 570
 ASTM D 792

ASTM D 2671
 ASTM D 638
 ASTM D 2671 C
 UL 224

AMS-DTL-7444
 AMS-DTL-23053/5
 ASTM D 2671 B

ASTM D 2671
 ASTM D 257

TYPICAL VALUES

13 N/mm²
 300%
 ≤+1%, ≤-10%; ≤+5%, ≤-10% (clear)
 0.20%
 1.45 g/cm³

-55° C to +135° C
 > 90° C
 no dripping, cracking or flowing
 elongation 200%
 no cracking
 pass (colours only)

no growth
 good
 no corrosion

20 kV/mm
 10¹⁴ ohm cm